PRODUCT

Conformity Data Sheet

ST 020/E ISSUED EN-00-02/22



GREENTANK SA 3 MM

| TECHNICAL CHARACTERISTICS | | | | |
|---|--|---------|-------------------|--------------|
| CHARACTERISTIC | TEST METHOD | UNITS | NOMINAL VALUES | TOLERANCES |
| Visible defects | EN 1850-1 | visible | Without defects | |
| Length | EN 1848-1 | m | 10,00 -1 | MLV |
| Width | EN 1848-1 | m | 1,000 -1% | MLV |
| Straightness | EN 1848-1 | mm | 20 mm x 10 m | Pass |
| Thickness | EN 1849-1 | mm | 3,0 | ± 10% |
| Watertightness (A) | EN 1928 | kPa | > 60 | MLV |
| External fire performance | EN 13501-5 | Class | F Roof | NPD |
| Reaction to fire | EN 13501-1 | Class | E | Pass |
| Shear resistence longitudinal / transversal | EN 12317-1 | N/50 mm | 550 / 450 | ± 20% |
| Tensile Strenght Longitudinal / Transversal | EN 12311-1 | N/50 mm | 600 / 500 | ± 20% |
| Elongation at break Longitudinal / Transversal | EN 12311-1 | % | 35 / 35 | - 15 absolut |
| Resistance to impact | EN 12691 | mm | 700 | MLV |
| Resistance to static loading Method A | EN 12730 | Kg | 15 | MLV |
| Resistance to tearing (nail shank) | EN 12310-1 | N | 200 / 200 | - 30% |
| Dimensional stability Longitudinal / Transversal | EN 1107-1 met. A | % | ± 0,3 % | MLV |
| Flexibility al low temperature | EN 1109 | °C | -25 | MLV |
| Flow resistance at elevated temperature | EN 1110 | °C | 100 | MLV |
| Durability of waterthigness against chemicals | EN 1847 / EN 1928 | Кра | > 60 | MLV |
| Artificial Ageing by long time exposure to UV ray combined to high temperature and heat. Resistance to water penetration. | EN 1296 / EN 1928 | Class | > 60 | MLV |
| Self Adhesion properties | ASTM D 1000 | N/10 mm | 20 | -5 |
| Determination of water vapour transmission properties - Water vapour resistance factor (μ) | EN 1931 | - | 120.000 | MLV |
| Determination of water vapour transmission properties - Water vapor diffusion (Sd) | EN 1931 | m | 360 | MLV |
| Minimum value of recycled content | EN ISO 14021 | % | 12 | MLV |
| FURTHER INFORMATION | | | | |
| Notification code | 1381 | | | |
| Certificate number | 1381-CPR-381 | | | |
| Reference norme | EN 13707 / EN 13969 | | | |
| Reinforcement | Polyester non-woven polyester fabric reinforced with glass fibers | | | |
| Compound | Upper compound: Innovative H.R.C. (High Recycled Content) compound with a specific formulation consisting of bitumen modified with high quantities of special polymers coming from the most modern recycling plants. Specially selected by General Membrane's Research and Development laboratory, these polymers guarantee excellent compatibility with bitumen, maintaining the same performance of the standard bituminous waterproofing compounds and lowering environmental impact. Lower compound: Elastomer (SBS) modified bitumen self adhesive. | | | |
| Surface Finishing | Upper surface: Gentex, polypropilene textured film and silicon release film on the overlap area. Lower surface: silicon release film | | | |
| Application method | Lay down the membrane by removing the protective silicon film, roll the overlaps with the apposite roller. If is necessary dry the upside part of the joint area with hot hair. | | | |
| Field of application | Foundation and tanking: post applied on retaining walls combined with thermal insulation | | | |
| 7.a 7.b Image: Constraint of the state of | | | | |

In terms of the Italian Ministerial Decree n° 65 of 14th March 2003, which sets out 'Classification, labelling and packaging of dangerous preparations in execution of the Directives issued by the Council and by the Commission of the European Community' the product does not contain dangerous elements. In according with the norm EN 13707 (October 2004) the water vapour transmission factor µ can be taken as >20.000. All membranes made by GENERAL MEMBRANE SAA are manufactured by using unblown asphalt and do not contain tar from coal, asbestos, chlorine, used and/or rerefined, are recyclable and are not dangerous waste. The release of a safety data sheet for this product is not compulsory, in any case an informative document is available for the correct use of the product.



GENERAL MEMBRANE S.p.A. Via Venezia 538, 30022 Ceggia (Venezia) Italia – Tel.+39 0421 322000 – Fax +39 0421 322800 – www.generalmembrane.it – info@generalmembrane.com